Lacquered Wood

6x36 Porcelain





04LACWHI636G

04LACBLA636G





04LACHON636G

04LACVIN636G





04LACNAT636G

04LACCHE636G



Tile: 6x36

For more information and images:

Lacquered Wood

Porcelain













Technical Characteristics

Specs	Test Method	Industry Standard	Test Result	
Water Absorption	ASTM C373	≤ 0.5%	≤ 0.4%	
Surface Wear Resistance	ANSI A137.1	Surface wear resistance properties of glazed vitreous and porcelain tile.	All Commercial / Residential	
Chemical Resistance	ASTM C650	No tile sample shows visible defects after continuous contact with a variety of chemicals for 24 hours.	Not Affected	
DCOF (Wet)	ANSI A326.3	≥ 0.42	≥ 0.42	
Stain Resistance	ASTM C1378	Surfaces are exposed to staining agents for 24 hours followed by four cleaning procedures.	Not Affected	
Breaking Strength	ASTM C648	≥ 250 lbf	≥ 300 lbf (8 mm); ≥ 400 lbf (10 mm)	
Freeze Resistance	ASTM C1026	No tile sample shows visible defects after repeated processes of freezing and thawing.	Resistant	
Warnaga Edga	ASTM C485	1.0.400/ or 1.0.05 in (1.1.9 mm)	<u>+</u> 0.40%	Rectified
Warpage Edge		± 0.40% or ± 0.05 in (± 1.8 mm)	<u>+</u> 0.50%	Calibrated
Warpage Diagonal	ASTM C485	1.0.400/ or 1.0.07 in (1.1.9 mm)	± 0.40%	Rectified
		± 0.40% or ± 0.07 in (± 1.8 mm)	<u>+</u> 0.50%	Calibrated
Modeline	ASTM C502	10.25% or 10.02 in (10.02 mm)	± 0.25%	Rectified
Wedging		± 0.25% or ± 0.03 in (± 0.8 mm)	± 0.50%	Calibrated
Thickness	ASTM C499	Range: ± 0.04 in	≤ 0.04 in	
Recycled Content		As reported	≥ 45% Pre-Consumer	

Nominal Size	Actual Size	Thickness	Finish	Rectified
6" x 36"	5.91" x 35.43"	8 mm	Glossy	-

Installation Note: Due to its linear plank shape, this material requires particular care when it comes to installation. The tile will look its best when offset is less than 33%. The staggered installation will minimize lippage which is common in tiles of this format. No claim will be honored after installation.

